

**PRODUCT DESCRIPTION** A one pack alkyd primer containing zinc phosphate anticorrosive pigment.

**INTENDED USES** As a general purpose conventional primer for application to internal steelwork.  
For use at Newbuilding.

**PRODUCT INFORMATION**

<b>Colour</b>	CPA536-Red, CPA537-Grey, CPA538-White
<b>Finish/Sheen</b>	Not applicable
<b>Part B (Curing Agent)</b>	Not applicable
<b>Volume Solids</b>	57% ±2% (ISO 3233:1998)
<b>Mix Ratio</b>	Not applicable
<b>Typical Film Thickness</b>	80 microns dry (140 microns wet)
<b>Theoretical Coverage</b>	7.13 m <sup>2</sup> /litre at 80 microns dft, allow appropriate loss factors
<b>Method of Application</b>	Airless Spray, Brush, Conventional Spray, Roller
<b>Flash Point</b>	Single Pack 35°C

Drying Information	-5°C	5°C	25°C	35°C
Touch Dry [ISO 1517:73]	4 hrs	60 mins	45 mins	30 mins
Hard Dry [ISO 9117:90]	7 days	5 days	3 days	2 days

Overcoating Data - see limitations	Substrate Temperature							
	-5°C		5°C		25°C		35°C	
Overcoated By	Min	Max	Min	Max	Min	Max	Min	Max
Interlac 542	48 hrs	ext	48 hrs	ext	24 hrs	ext	16 hrs	ext
Interlac 665	48 hrs	ext	48 hrs	ext	24 hrs	ext	16 hrs	ext
Intertherm 891	48 hrs	ext	48 hrs	ext	24 hrs	ext	16 hrs	ext

**Note** The primer surface must be freshwater washed to extend the maximum overcoating interval if outside exposure exceeds 28 days.

**REGULATORY DATA**

<b>VOC</b>	348 g/lit calculated 226 g/kg of liquid paint as supplied. EU Solvent Emissions Directive (Council Directive 1999/13/EC)
------------	---

**Note:** VOC values are typical and are provided for guidance purposes only. These may be subject to variation depending on factors such as differences in colour and normal manufacturing tolerances.

**CERTIFICATION**

When used as part of an approved scheme, this material has the following certification:

- Fire Resistance - Surface Spread of Flame (WFR) - (BS476:Part 7)
- Fire Resistance - Surface Spread of Flame (WFR) - (IMO Resolution A653 (16))
- Food Contact - Carriage of Grain (NOHA)
- Fire Resistance - Marine Equipment Directive compliant

Consult your International Paint representative for details.

---

**SYSTEMS AND  
COMPATIBILITY**

Consult your International Paint representative for the system best suited for the surfaces to be protected.

---

**SURFACE  
PREPARATIONS**

Use in accordance with the standard Worldwide Marine Specifications.

All surfaces to be coated should be clean, dry and free from contamination.

High pressure fresh water wash or fresh water wash, as appropriate, and remove all oil or grease, soluble contaminants and other foreign matter in accordance with SSPC-SP1 solvent cleaning.

**NEWBUILDING**

Where necessary, remove weld spatter and smooth weld seams and sharp edges.

Clean welds and damaged shop primer by power tooling to Pt3 (JSRA SPSS:1984).

Consult your International Paint representative for specific recommendations.

**NOTE:**

**For use in Marine situations in North America, the following surface preparation standards can be used:  
SSPC-SP3 in place of St3 (ISO 8501-1:2007)**

**APPLICATION**

<b>Mixing</b>	This material is a one pack coating and should always be mixed thoroughly with a power agitator before application.
<b>Thinner</b>	Not Recommended. Use International GTA004 only in exceptional circumstances (max 5% by volume). DO NOT thin more than allowed by local environmental legislation.
<b>Airless Spray</b>	Recommended Tip Range 0.46-0.53 mm (18-21 thou) Total output fluid pressure at spray tip not less than 176 kg/cm <sup>2</sup> (2500 p.s.i.)
<b>Conventional Spray</b>	Suitable. Use suitable proprietary equipment. Thinning may be required.
<b>Brush</b>	Suitable. When applying Interprime 538 by brush, it may be necessary to apply multiple coats to achieve the total specified system dry film thickness.
<b>Roller</b>	Suitable. When applying Interprime 538 by roller, it may be necessary to apply multiple coats to achieve the total specified system dry film thickness.
<b>Cleaner</b>	International GTA004
<b>Work Stoppages and Cleanup</b>	Thoroughly flush all equipment with International GTA004. All unused material should be stored in tightly closed containers. Partially filled containers may show surface skinning and/or a viscosity increase of the material after storage. Material should be filtered prior to use.
<b>Welding</b>	In the event welding or flame cutting is performed on metal coated with this product, dust and fumes will be emitted which will require the use of appropriate personal protective equipment and adequate local exhaust ventilation. In North America do so in accordance with instruction in ANSI/ASC Z49.1 "Safety in Welding and Cutting."

**SAFETY**

**All work involving the application and use of this product should be performed in compliance with all relevant national Health, Safety & Environmental standards and regulations.**

**Prior to use, obtain, consult and follow the Material Safety Data Sheet for this product concerning health and safety information. Read and follow all precautionary notices on the Material Safety Data Sheet and container labels. If you do not fully understand these warnings and instructions or if you can not strictly comply with them, do not use this product. Proper ventilation and protective measures must be provided during application and drying to keep solvent vapour concentrations within safe limits and to protect against toxic or oxygen deficient hazards. Take precautions to avoid skin and eye contact (ie. gloves, goggles, face masks, barrier creams etc.) Actual safety measures are dependant on application methods and work environment.**

**EMERGENCY CONTACT NUMBERS:**

**USA/Canada - Medical Advisory Number 1-800-854-6813**

**Europe - Contact (44) 191 4696111. For advice to Doctors & Hospitals only contact (44) 207 6359191**

**R.O.W. - Contact Regional Office**

**LIMITATIONS**

This product should not be used on external steelwork.

Overcoating information is given for guidance only and is subject to regional variation depending upon local climate and environmental conditions. Consult your local International Paint representative for specific recommendations. Apply in good weather. Temperature of the surface to be coated must be at least 3°C above the dew point. For optimum application properties bring the material to 21-27°C, unless specifically instructed otherwise, prior to mixing and application. Unmixed material (in closed containers) should be maintained in protected storage in accordance with information given in the STORAGE Section of this data sheet. Technical and application data herein is for the purpose of establishing a general guideline of the coating application procedures. Test performance results were obtained in a controlled laboratory environment and International Paint makes no claim that the exhibited published test results, or any other tests, accurately represent results found in all field environments. As application, environmental and design factors can vary significantly, due care should be exercised in the selection, verification of performance and use of the coating.

In the overcoating data section 'ext' = extended overcoating period. Please refer to our Marine Painting Guide - Definitions and Abbreviations available on our website.


UNIT SIZE	Unit Size	Vol	Pack
	20 lt	20 lt	20 lt
<i>For availability of other unit sizes consult International Paint</i>			
UNIT SHIPPING WEIGHT	Unit Size	Unit Weight	
	20 lt	32.8 Kg	
STORAGE	Shelf Life	24 months minimum at 25°C. Subject to reinspection thereafter. Store in dry, shaded conditions away from sources of heat and ignition	

**WORLDWIDE AVAILABILITY**

Consult International Paint.

**IMPORTANT NOTE**

*The information in this data sheet is not intended to be exhaustive; any person using the product for any purpose other than that specifically recommended in this data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at their own risk. All advice given or statements made about the product (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability at all for the performance of the product or for (subject to the maximum extent permitted by law) any loss or damage arising out of the use of the product. We hereby disclaim any warranties or representations, express or implied, by operation of law or otherwise, including, without limitation, any implied warranty of merchantability or fitness for a particular purpose. All products supplied and technical advice given are subject to our Conditions of Sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is liable to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to check with their local International Paint representative that this data sheet is current prior to using the product.*

 **International** and product names mentioned in this data sheet are trademarks of, or are licensed to, AkzoNobel.

© AkzoNobel, 2009

[www.international-marine.com](http://www.international-marine.com)